

### Natural Flake Graphite for Friction Applications

**Product Name: LDI-NFG 20X50FR**

**Country of Origin**

Canada

**General Characteristics**

Formula: Carbon

Aspect: Fine black powder

CAS number: 7782-42-5

**Standard Packaging**

25 kg paper bags, 40 bags/pallet (1000 kg)

25 kg paper bags, 36 bags/pallet (900 kg)

50 lbs paper bags, 40 bags/pallet (2000 lbs)

1000 kg big bags, 1000 kg/pallet

**Available Carbon Grades**

From 94% to 97%

**Northern Graphite Corporation**

Suite 802, 3030 boul Le Carrefour

Laval, Quebec, Canada H7T 2P5

T +1-438-688-0007

[clients@northerngraphite.com](mailto:clients@northerngraphite.com)

This product is in compliance with the EC Directive 2002/95/CE (Restriction Of Hazardous Substances, RoHS). The information contained herein is believed to be correct. However, no warranty is made, either expressed or implied regarding the accuracy or the results to be obtained from the use of such information. The user assumes all risk and liability for intellectual property infringement and no statement(s) made in relation to this material is intended or shall be construed as inducing infringement of a valid patent.

DEC 2023

**Guaranteed Values**

Bulk Density: 0.37 – 0.96 g/cm<sup>3</sup>

Moisture: 0.5% max

Cumulative +50 mesh: 80% min  
(+300 micron)

**Typical Values**

**Ash Analysis**

SiO <sub>2</sub> :	41.9%
Fe <sub>2</sub> O <sub>3</sub> :	14.4%
Al <sub>2</sub> O <sub>3</sub> :	14.6%
CaO:	16.5%
MgO:	7.1%
K <sub>2</sub> O:	1.6%
Na <sub>2</sub> O:	1.0%
TiO <sub>2</sub> :	0.3%
MnO:	0.1%
P <sub>2</sub> O <sub>5</sub> :	0.1%
S:	2.1%
Trace:	0.4%
TOTAL:	100%

These are typical values provided for information purposes. Individual Lots may vary.

**Particle Size Distribution**

(vibrated sieving)

20x50	Average %	Minimum %	Maximum %
+20 Mesh	1	0	3
-20/+40 Mesh	31	14	46
-40/+50 Mesh	52	39	67
-50/+60 Mesh	10	0	15
-60/+80 Mesh	3	0	7
-80 Mesh	3	0	8

These are typical values provided for information purposes. Individual Lots may vary.